

DW-62L 100%CO₂ EN ISO 17632-A-T 50 6 Z P C 2 H5

AWS A5.29 E91T1-Ni2C-J


Description and Application


DW-62L is a rutile flux cored wire specially formulated to meet the rigorous demands for 500 MPa yield strength class low temperature service steels, as found in the offshore and shipbuilding industries.

Not only does this wire have excellent CTOD values at the standard -10°C test temperature, but it also has excellent CTOD values at the very severe test temperature of -40°C.

This wire is applied to the welding of medium to heavy section butt or fillet weld joints.

Recommended Parameter Range, for flat position






Typical Chemical Analysis (wt. %)

| C | Si | Mn | Р | S | Ni | Cr | Mo |
|------|------|------|-------|-------|-----|----|----|
| 0.08 | 0.27 | 1.32 | 0.009 | 0.007 | 2.6 | - | - |

Typical Mechanical Properties

| | R _e (MPa) | R _m (MPa) | A ₅ (%) | CV(J)-60°C |
|----------|----------------------|----------------------|--------------------|------------|
| | 601 | 660 | 25 | 100 |
| Guaranty | min.500 | 560~720 | min.18 | min.47 |

Welding Positions



Approvals

| LR | DNV GL | BV | ABS | R.M.R.S | Others |
|----|--------|----|-------------|------------|--------|
| - | - | - | 5YQ500SA H5 | 5Y50 MS H5 | - |